

TECHNICAL DATA SHEET

Issue: 2

Version: 1

BK-Dur XPS**RZ-TLP-131-01****Date: 04.06.2024.****Prepared:** Jasmina Obradović**Approved:** Lena Riznić

1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

Commercial product name: BK-Dur XPS**Information on the manufacturer:**

Banja Komerc Bekament DOO
Kralja Petra Prvog 132, Banja, Arandjelovac
34304 Banja
tel. 034-6777-500
fax. 034-6777-505
e-mail: office.prodaja@bekament.com

Contact for TDS preparation: e-mail: lena.riznic@bekament.com
kk.eps@bekament.com

2. DESCRIPTION AND SCOPE OF APPLICATION

BK-Dur, waffle is a thermal insulation board made of extruded polystyrene foam, ribbed surface structure, resistant to water (moisture) and high pressure loads. It is intended for insulation of new buildings and renovation of existing buildings. Hard-pressed polystyrene foam boards with a closed-cell structure allow the building to "breathe". This is achieved by a special mixture and composition of cells in combination with the treated surface. It is used for insulation of foundations, insulation of floors with high pressure load, perimeter insulation, insulation of flat roofs.

3. COMPOSITION

Chemical composition: Extruded polystyrene

4. TECHNICAL CHARACTERISTICS

Boards dimensions: Boards are 1250 x 600 mm thick, 20 mm and 120 mm thick, with straight edges or folded edges.

Packing of boards: The boards are packed in packages, volume 0.27m³ to 0.30 m³, wrapped in opaque PE foil.

Application temperature: up to 75 °C

Product label key: for thickness 20 mm:

EN 13164:2012: XPS-EN 13164-T1-CS(10/Y)200-DS(TH)-WL(T)0,7-WD(V)3-TR400
for thickness 30 mm:

EN 13164:2012: XPS-EN 13164-T1-CS(10/Y)250-DS(TH)-WL(T)0,7-WD(V)3-TR400

RZ-TLP-131-01

Banja Komerc Bekament d.o.o., Banja / 34304 Arandjelovac | www.bekament.com

TECHNICAL DATA SHEET

Issue: 2

Version: 1

BK-Dur XPS
RZ-TLP-131-01
Date: 04.06.2024.
Prepared: Jasmina Obradović

Approved: Lena Riznić

for thickness 40 mm to 80 mm:

EN 13164:2012: XPS-EN 13164-T1-CS(10/Y)300-DS(TH)-WL(T)0,7-WD(V)3-TR400

for thickness 100 mm to 120 mm:

EN 13164:2012: XPS-EN 13164-T1-CS(10/Y)300-DS(TH)-WL(T)1,5-WD(V)3-TR400

Characteristic	Label	Unit	Declared	Tolerance	Harmonized technical specification
Dimensional tolerance for thickness <50 mm	T	mm	T1	-2 / +2	EN 29469
Dimensional tolerance for thickness 50 mm to 120 mm	T	mm	T1	-2 / +3	EN 29469
Compressive strength for 20mm	CS(10/Y)	kPa	CS(10/Y)200	≥200	EN 29469
Compressive strength for 30mm	CS(10/Y)	kPa	CS(10/Y)250	≥250	EN 29469
Compressive strength for 40mm to 120mm	CS(10/Y)	kPa	CS(10/Y)300	≥300	EN 29469
Water absorption, 7 days, complete immersion, method 2A	WL(T)	%	WL(T)0,7	≤0,7	EN 16535
Allowable compressive stress for permanent load of 50 years with deformation <2%	CC (2/1,5/50)	kPa	CC (2/1,5/50)130	130	EN 16534
Behavior at 40kPa load and temperature 70°C	DLT	%	DLT (2)5	<5	EN 1605
Resistance to cyclic thawing-	FTCDi		FTCD1	1	EN 16546

TECHNICAL DATA SHEET

Issue: 2

Version: 1

BK-Dur XPS
RZ-TLP-131-01
Date: 04.06.2024.
Prepared: Jasmina Obradović

Approved: Lena Riznić

freezing after long-term diffuse absorption of water					
Classification of reaction to fire			Class E		EN 13501-1
Heat resistance	R _d	m ² K/W	see in table 2		EN 12667
Water absorption by diffusion	WD(V)	%	3	≤3	EN16536
Tensile strength perpendicular to the surface	TR	kPa	TR400	≥400	EN 1607
Thermal conductivity coefficient	Λ _d	W/mK	see in table 2	/	EN 12667

Plate thickness, mm	d	20	30	40	50	60	70	80	90	100	110
Lambda		0,0304	0,0318	0,0330	0,0330	0,0330	0,0340	0,0340	0,0340	0,0340	0,0340
Lambda / thickness W / m ² K	λ _D /d										
Thermal resistance, m ² K / W	R _D	1,52	1,06	0,83	0,66	0,55	0,49	0,43	0,38	0,34	0,31
		0,65	0,90	1,20	1,50	1,80	2,05	2,35	2,65	2,90	3,20

5. OTHER CHARACTERISTICS

Appearance: blue, compact material.

Odor: The appearance of a slightly unpleasant odor only when cutting with heated objects. Smell and minimal fumes and then harmless.

6. INSTALATION

The product should be applied up to the recommended temperature. When exposed to a higher temperature than recommended, which is a maximum of 75C, the boards can soften, permanently deform, change dimensions, melt or become brittle and lose mechanical properties.

RZ-TLP-131-01

 Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET

Issue: 2

Version: 1

BK-Dur XPS**RZ-TLP-131-01****Date: 04.06.2024.****Prepared:** Jasmina Obradović**Approved:** Lena Riznić

The product can only be glued with adhesives based on cement, bitumen or plastic materials. The adhesive must not contain chemically soluble agents, which can react with the plates in a way that softens them, causes shrinkage and even dissolution, which can result in the loss of basic properties.

The product is installed in accordance with the general rules for performing thermal insulation works in construction.

7. HANDLING AND STORAGE

No special precautions are required for use. The product is not classified as hazardous for transport. Take care not to damage the plates.

The product, from the aspect of the influence of atmospheric precipitation, can also be stored outdoors because it does not absorb moisture, but it should be protected from the strong sun, preferably in the original packaging.

Slabs should not be exposed to flammable sources. Exposure to strong sunlight, after some time, can cause the surface layer to turn into dust.

8. PERSONAL PROTECTION

Respiratory protection: Not required

Hand and body protection: Preventive use of protective gloves is recommended in case of repeated skin contact.

Eye protection: Does not irritate the eyes even if the part happens to get into the eye. Goggles can be used preventively.

Fire protection: Dry extinguishing media, light foam and water mist are recommended

9. ECOTOXICOLOGICAL INFORMATION

Based on experience and existing information, no adverse effects on human health or the environment are known when used properly.

10. DISPOSAL METHOD

In accordance with local/regional/European/national regulations.

11. OTHER INFORMATION

If the contractor notices an aesthetic or application deficiency while using the material, he is obliged to cease the works and notify the manufacturer thereof, who shall take the remarks into consideration in the shortest possible time frame. Remarks sent to the manufacturer after incorporation of a significant portion or the entire quantity of the material, cannot be the subject of complaint.

TECHNICAL DATA SHEET

Issue: 2

Version: 1

BK-Dur XPS**RZ-TLP-131-01****Date: 04.06.2024.****Prepared:** Jasmina Obradović**Approved:** Lena Riznić

12. NOTE

Banja Komerc Bekament DOO performs product quality checks using its own laboratories. It also regularly tests its products in certified laboratories. The Data Sheet is the product of our knowledge and previous practical experience and it should serve to all users as a recommendation in order to achieve the best possible results. If weather and other conditions are different than those described in our instructions, our instructions need to be taken as general guidelines, without an installation warranty.

Banja Komerc Bekament DOO assumes no liability for damages resulting from the improper use or incorrect selection of product, as well as for poorly executed works. It is assumed that the contractor has mastered the techniques of incorporation and use of various products.

Matters written herein bind us in no way.

Date of production: 04.06.2024.

Previous version: 26.02.2024.

Changed chapters: 4