

1. PRODUCT AND COMPANY INFORMATION

Commercial product name: BK-Fas Silicon

Manufacturer:

Banja Komerc Bekament DOO
Kralja Petra Prvog 132
34304 Banja
Arandelovac
tel. 034-6777-500
fax. 034-6777-505
e-mail: komercijala@bekament.com

TDS contact: email: laboratorija@bekament.com

2. DESCRIPTION, FIELD OF APPLICATION

BK-Fas Silicon is paint based on a silicone resin and high-quality acrylic emulsion. It is characterized by excellent waterproof abilities, vapor permeability, and good coverage. It is also very resistant to UV radiation and weather. It can be used for the decorative protection of new facades, as well as painting over quality facades, bearing walls, and old facade walls. Due to its excellent resistance, it is also used for application on the internal walls of public objects. As the result of a specific composition, the paint is characterized by good resistance to wear and tear, dust, and other impurities.

It is considered an environmentally friendly wall paint not harmful to human health or the environment. It does not contain organic solvents.

3. COMPOSITION

Chemical composition: Silicone resin-based binder, aqueous polymer emulsion, water, additives, pigments, mineral fillers.

Hazardous substances: In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, this product is not classified as a hazardous product.

4. TECHNICAL CHARACTERISTICS

Density, g/dm³ (EN ISO 2811-1)	1,500-1,600
Viscosity, mPas (EN ISO 2555)	20,000-30,000
Adhesion to the surface , MPa (EN ISO 4624)	≥1.5

TECHNICAL DATA SHEET	Edition: 2	Version: 2
BK-FAS SILICON	RZ-TLP-037	Date: 19.10.2021.

Water absorption, kg/(m² h^{0,5}) (EN 1062-3)	≤0,1 (class W ₃ according to EN 1062-1)
Vapor permeability m (EN ISO 7783-2)	<0,14 (class V ₁ according to EN 1062-1)
Particle size, μm (EN 1524)	< 100 (fine according to EN 13300)
Coating thickness, μm (EN ISO 3233)	100-200 (Class E ₃ according to EN 1062-1)
Indicative consumption, g/m²	150-250
Packaging, kg	1; 3; 5; 15;

Viscosity, mPas (EN ISO 2555)	20000-25000
Gloss, % (EN 2813)	< 5 at an angle 85° (deep mat according to EN 13300)

5. OTHER CHARACTERISTICS

Physical appearance: White or colored viscous liquid
Odor: Specific of polymeric binders

pH value (EN ISO 787-9): 7.5-8.5

Dry matter content (EN ISO 3251), %: ~70

VOC* content, g/l: < 1 (maximum allowed value A (c) 40 g/l)

*VOC: Volatile Organic Compound;

Possibility of choosing 144 shades according to Bekament's 2012 color charts. We do not guarantee a complete match according to the color charts of other manufacturers, nor do we guarantee absolute repeatability of shades.

6. SURFACE PREPARATION

The surface to which the paint is applied must be firm, clean, and dry, without poorly bound parts, greasy stains, etc. Appropriate base are all surface of lime, cement, and cement-lime mortars (at least one month old), concrete surfaces (at least one month old), surfaces smoothed out with quality leveling masses (the age depends on the type), as well as surfaces with colors or mortars which have taken on dispersion colors, etc. Before applying, the surface must be coated using the BK-Ultra Prime or BK-Grund Universal primer, preferably in the same color of the dispersion paint. The primer must be left to dry before applying the paint for at least 12 hours. In case when mould-infested surfaces are to be painted, it is necessary to disinfect them by using BK-Sanicid.

RZ-TLP-037

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

In the case of painting the surfaces who are painted with oil-based paints, varnishes, etc, a complete removal of all existing spreads must be performed.

Great care should be given to preparing the basis, especially when it comes to painting over damaged facades. Any irregularities in the surface texture will prevent a satisfactory result to be achieved. Most of the time, irregularities become even more visible after being painted over.

7. PREPARATION AND APPLICATION

The mass must be stirred before use, and homogenization of materials from different batches/packages must be performed. After that, dilute the mass as needed with about 10 % of water. The paint is applied using a long-haired roller or brush, most often in two layers.

Application of the second layer is done after the first layer is completely dry. In normal conditions (T=+23-25 °C, relative humidity=50-60 %), this takes 4-6 hours.

Work must be even and without interruptions in continuous wall surfaces so as to avoid any irregularities created due to the adhesion of surfaces, irregular drying, etc. Subsequent color corrections during application (diluting additionally, adding pigments and the like) are not allowed.

Air and surface temperature during installation should be in the +5 °C to +30 °C range. Do not work under direct sunlight, wind, or rain. High moisture and low temperatures may significantly lengthen the drying time.

After 4 hours of drying in normal conditions (T=+23-25 °C, relative humidity = 50-60 %), the paint is dry when touched, whereas the full resistance of the material is achieved after 3 weeks. Resistance to precipitation is achieved after at least 24 h of drying in normal conditions. High moisture and low temperatures may significantly prolong the paint drying time and affect the shade uniformity.

8. MAINTENANCE

Surfaces painted over using BK-Fas Silicon are resistant to wear and tear and do not require any particular maintenance. It is recommended that the surface is occasionally dusted off. Any possible impurities may be removed using warm water and a universal house cleaning supply (laundry detergent/dish soap). After that, rinse the surface using clean water. No cleaning or washing using abrasive products or tools is permitted. If stains or impurities still exist, re-painting the facade surface is possible. This may be done using the BK-Fas Silicon or BK-MicroFas Silicon.

Regular maintenance of facade surfaces also reduces the risk of appearance of algae and fungi. Appearance of microorganisms is characteristic of thermal insulation systems. This mainly happens on objects close to trees, rivers, lakes, in areas with frequent periods of fog and higher humidity, in valleys, etc. Objects which are in direct contact with soil saturated with moisture or dries slower, objects with shorter roofs, all

objects where works around openings were poorly done, etc. are all at risk. Western and northern sides of the object are the ones under most stress.

Some measures of suppressing/reducing the risk of microorganisms developing are cleaning the facade surfaces on a regular basis, removing surface waters around the object, cleaning the snow, controlling drainage around the object, cleaning gutters, etc. Remediation of infected surfaces is not only performed on surfaces where microorganisms are visible; the entire wall is treated. Treatment should be performed according to the instructions listed in the Product Data Sheet for BK-Sani Cid. Upon the removal of microorganisms, treated surfaces must be painted over using facade paint with the addition of a biocidal product for the protection of dry film. Regardless of the adequate function of the biocidal product, there is no guarantee that the microorganisms will not reappear after a certain period of time. Special emphasis needs to be placed on the fact that the appearance of microorganisms cannot be fully prevented; it can only be slowed down. The effect of the biocidal product wanes off during time. Objects located in conditions which make them susceptible to the development of microorganisms must be regularly maintained and periodically painted over in the previously described manner.

It is common that spiders and insects gather on the surface of thermal insulation systems. This is considered as soiling. The abovementioned regular maintenance is a preventative measure in this case, too. In the end, it is necessary to point out that the appearance of microorganisms, spiders, insects, etc. on facades is purely an aesthetic problem, not a functional one. As such, it may not serve as a basis of claims regarding the quality of the thermal insulation system.

9. CLEANING THE TOOLS

All tools must be thoroughly washed using water immediately after use. If the tools are not washed immediately after use, remove the hardened residue mechanically. Removal may be easier if the tools are submerged in water over a period of several hours.

10. HANDLING AND STORAGE

No special caution during use is needed when using the product properly. Keep out of reach of children.

Store at temperatures between +5 ° C and +25 ° C, protected from direct sunlight and frost.

Shelf life: 18 months.

11. PERSONAL PROTECTION

Respiratory tract protection: Not needed when the rooms are well aerated.

Hands and body protection: When the skin is repeatedly exposed to the mass, a preventative use of protection gloves is recommended. Use long-sleeve work overalls.

Eye protection: Use safety goggles as a preventative measure.

TECHNICAL DATA SHEET	Edition: 2	Version: 2
BK-FAS SILICON	RZ-TLP-037	Date: 19.10.2021.

12. ECOTOXICOLOGICAL INFORMATION

Based on experiences and information currently available, no negative health effects are known when the product is used appropriately. Prevent uncontrolled discharge into sewage and waterways.

13. STORAGE

In accordance with local/regional/European/national regulations.

14. OTHER INFORMATION

The color chart was printed on paper. While applying the product onto various surfaces, certain smaller deviations from the color chart may be expected. These deviations are not subject to claims. Certain deviations of the paint in relation to the appropriate shade in the color chart are possible due to the use of natural mineral fillers. The uneven color shading of a facade surface painted over may be the consequence of inappropriate conditions at installation, differences in absorption, and the roughness of the base.

All paint for a single object must be ordered at one time. Banja Komerc Bekament DOO does not guarantee a complete match of shades from various batches. Deviations in terms of tone are not subject to claims.

If the contractor notices an aesthetic or application deficiency while using the material, he is obliged to cease the works and notify the manufacturer of this. The manufacturer will consider the claim in the shortest possible time frame. Complaints to the manufacturer upon using a significant portion or the entire amount of the materials are not subject to claims.

While choosing the shade to be installed into the thermal insulation system, we recommend shades with luminous intensity Y above 30. Colors of intense shades, are less resistant to wash out due to rainfall. They are also less likely to maintain their color consistency over extended period of time. Changes in facade surfaces which occur due to external factors cannot be the object of claims.

15. NOTE

Banja Komerc Bekament DOO performs product quality checks using its own laboratories. It also regularly tests its products in certified laboratories. The Data Sheet is the product of our knowledge and previous practical experience. The purpose of the Data Sheet is to serve as a recommendation in order to achieve the best possible results. If weather and other conditions are different than those described in our instructions, our instructions need to be taken as general guidelines, without an installation warranty.

Banja Komerc Bekament DOO assumes no liability for damages resulting from the improper use or incorrect product selection, as well as for poorly executed work. It is

RZ-TLP-037

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET	Edition: 2	Version: 2
BK-FAS SILICON	RZ-TLP-037	Date: 19.10.2021.

assumed that the contractor has mastered the techniques of installing and use of various products.

Matters written herein bind us in no way.

This document replaces all previous versions, which as of the above date of making of this one are considered invalid.

Date: February 4 2013

Previous version: Version 2,1 – November 5 2020

Amended chapters 1,6