

1. PRODUCT AND COMPANY INFORMATION

Commercial product name: BK-GletEx S

Manufacturer:

Banja Komerc Bekament DOO
Kralja petra Prvog 132
Arandelovac
tel. 034-6777-500
fax. 034-6777-505
email: komercijala@bekament.com

TDS contact: email: laboratorija@bekament.com

2. DESCRIPTION, FIELD OF APPLICATION

BK-GletEx S is a micro-reinforced powdery mineral-based skim coat mass used for thin – layer smoothing out wall surfaces in the external environment. It is manually applied in the total thickness of up to 5 mm. It can also be used for smoothing interior surfaces.

3. COMPOSITION

Chemical composition: Lime, white Portland cement, polymer binder, microfibers, additives, mineral fillers.

Hazardous substances: In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, components of the Portland cement and lime are hazardous substances. The product is therefore classified a hazardous one with the following label: Hazard.

4. TECHNICAL CHARACTERISTICS

Bulk density, g/dm³	800-900
Adhesion o the substrate, MPa (EN 1015-12)	>0,3
Compressive strength, MPa (EN 1015-11)	1,5-5,0 (klasa CS II accroding to EN 998-1)
Flexural strength, MPa (EN 1015-11)	>1,0
Capillary water absorption -c, kg/m² min^{0,5} (EN 1015-18)	≤0,2 (class W ₂ according to EN 998-1)
Thermal conductivity -λ_{10°C dry}, W/m.K (EN 1745 Table A.12)	0,36
Density of hardened mortar,, g/dm³ (EN 1015-10)	1250

TECHNICAL DATA SHEET	Edition: 2	Version: 2
BK-GLETEX S	RZ-TLP-030-02	Date: 09.08.2023.

Application thickness	max. 2 mm for one layer, total thickness max. 6 mm
Indicative consumption, kg/m²/mm	~1,0
Packaging, kg	5; 25

5. OTHER CHARACTERISTICS

Physical appearance: White powder

pH value of the fresh plaster mass: 11-13

Due to the specific composition, the plaster mass may act aggressively during subsequent applications of dispersion paints. It is therefore recommended to apply the appropriate bases before painting.

6. SURFACE PREPARATION

The surface to which the mass is applied must be firm, clean, and dry, without poorly bound parts, greasy stains, etc. The following surfaces are appropriate: cement-lime and gypsum-lime mortars (at least one month old), concrete surfaces (at least one month old), fiber-cement panels, as well as surfaces with non-soluble facade paints which have taken solid hold. In the case of application on quality mineral surfaces, as well as on well-accepted dispersion paints, it is first necessary to apply the BK-Ultra Prime substrate, in order to achieve better adhesion of the mass. In case the surface is excessively absorbent, impregnation using BK-Nivelator is recommended. In case of surfaces which are peeling, chipping and/or crumbling, it is necessary to remove all layers which are poorly bonded, and then impregnate the surface with BK-Penetrat.

In case of skimming the mould-infested surfaces, it is necessary to disinfect them by using BK-Sanacid. While uniforming surfaces in question that have been previously treated with oil-based paints, varnishes, etc, a complete removal of all existing spreads must be performed.

7. PREPARATION AND APPLICATION

Preparation of the mass is performed by lightly adding the powder into about 40 % of water (about 10l of water to 25 kg of powder or around 2 l of water to 5 kg of powder), with constant stirring using an electric blender until the mass becomes fully homogenized. The mass must be left to set for at least 10 minutes. After that, stir yet again and, if needed, add slightly more water in order to set the appropriate consistency. The mass is applied manually using a stainless metal trowel. Application is typically performed in two layers, each 1-3 mm thick, total thickness of up to 5 mm for a two-layer coating. Application of the second layer is done after the first layer is completely dry. In normal conditions (T=+23-25 °C, relative humidity=50-60 %), this takes 6-8 hours. Before applying the second layer, the first layer must be sanded off using fine sanding paper either manually or using a machine (choose the appropriate sanding paper, 180 to 240

fineness factor, depending on the technique and purpose). The same process must be applied with the final layer.

Air and basis temperature during installation should be in the +5 °C to +30 °C range. The prepared mass must be used within 2-3 hour.

8. CLEANING THE TOOLS

All tools must be thoroughly washed using water immediately after use. If the tools are not washed immediately after use, remove the hardened residue mechanically.

9. HANDLING AND STORAGE

The material must be transported in sealed bags. If the product is used in closed rooms, make sure the space is well ventilated. Protect your eyes and skin when working with wet plaster mass due to an alkaline reaction.

Store the material in dry rooms, on pallets, protected from moisture.

Shelf life: 12 months.

10. PERSONAL PROTECTION

Respiratory tract protection: In case the process causes excessive dust, use a face mask. Hands and body protection: Use safety gloves. Wash hands using water each time the work is interrupted. Use long-sleeve work overalls.

Eye protection: Use safety goggles in order to protect the eyes from the dust and wet plaster mass.

11. REGULATION INFORMATION

In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, components of the Portland cement and lime are hazardous substances. The product is therefore classified a hazardous one with the following label: Hazard



Hazard

Skin irritation, Category 2 : H315

Skin sensitization, Category 1 : H317

Heavy eye damage, Category 1 : H318

Specific target organ toxicity - single exposure, respiratory tract irritation, category 3: H335

H-labels:

H315 Causes skin irritation.

H317: May cause an allergic skin reaction.

H318 Causes serious eye damage.

H335 May cause respiratory irritation.

P-labels:

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352 IF ON SKIN: Wash with plenty of water.

P333+P313 If skin irritation or rash occurs: Get medical advice/attention.

P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P304+P340 IF INHALED: Remove person to fresh air and keep comfortable for breathing.

12. ECOTOXICOLOGICAL INFORMATION

Based on experiences and information currently available, no negative health effects are known when the product is used appropriately. Prevent uncontrolled discharge into sewage and waterways.

13. STORAGE

In accordance with local/regional/European/national regulations.

14. OTHER INFORMATION

If the contractor notices an aesthetic or application deficiency while using the material, he is obliged to cease the works and notify the manufacturer of this. The manufacturer will consider the claim in the shortest possible time frame. Complaints to the manufacturer upon using a significant portion or the entire amount of the materials are not subject to claims.

15. NOTE

Banja Komerc Bekament DOO performs product quality checks using its own laboratories. It also regularly tests its products in certified laboratories. The Data Sheet is the product of our knowledge and previous practical experience. The purpose of the Data Sheet is to serve as a recommendation in order to achieve the best possible results. If weather and other conditions are different than those described in our instructions, our instructions need to be taken as general guidelines, without an installation warranty.

TECHNICAL DATA SHEET	Edition: 2	Version: 2
BK-GLETEx S	RZ-TLP-030-02	Date: 09.08.2023.

Banja Komerc Bekament DOO assumes no liability for damages resulting from the improper use or incorrect product selection, as well as for poorly executed work. It is assumed that the contractor has mastered the techniques of installing and use of various products.

Matters written here in bind us in no way.

This document replaces all previous versions. All previous versions, starting with the listed date the document was compiled, are void.

Date: 09.08.2023.

Previous version: 2.1 – 24.12.2021.

Amendments Chapters: 1.