

<b>TECHNICAL DATA SHEET</b>	Issue: 1	Version: 2
<b>BK-LIV 30</b>	<b>RZ-TLP-151</b>	<b>Date: 24.12.2021.</b>

## 1. PRODUCT AND COMPANY INFORMATION

**Commercial product name:** BK-Liv 30

**Manufacturer:**

Banja Komerc Bekament DOO  
 Kralja Petra Prvog 132  
 Arandelovac  
 tel. 034-6777-500  
 fax. 034-6777-505  
 e-mail: [komercijala@bekament.com](mailto:komercijala@bekament.com)

**TDS contact:** email: [laboratorija@bekament.com](mailto:laboratorija@bekament.com)

## 2. DESCRIPTION, FIELD OF APPLICATION

BK-Liv 30 is a self-leveling, fast-setting, high strength mass used for leveling of concrete surface and cement screeds before applying parquets, ceramic tiles, PVC, and other types of floor tiling in residential, commercial and similar buildings. The product is not intended as a finishing layer. It is used for indoor and outdoor surfaces (for outdoor within the BK-Hidrostop water insulation coatings). BK-Liv 30 is suitable for use for systems with floor heating.

## 3. COMPOSITION

**Chemical composition:** Grey Portland cement, additives, mineral fillers.

**Hazardous substances:** In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, grey Portland cement is a hazardous substance. The product is therefore classified a hazardous one with the following label: Hazard

## 4. TECHNICAL CHARACTERISTICS

<b>Bulk density, g/dm<sup>3</sup></b>	1,200-1,400
<b>Flexural strength, MPa (EN 13892-2)</b>	≥ 7 (Class F7 according to EN 13813)
<b>Compressive strength, MPa (EN 13892-2)</b>	≥ 30 (Class C30 according to EN 13813)
<b>Resistance to wear and tear, cm<sup>2</sup> (EN 13892-5)</b>	≤ 15 Class RWA20 according to EN 13813)
<b>Indicative consumption, kg/m<sup>2</sup>/mm thickness</b>	≈ 1.5-1.7

RZ-TLP-027

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | [www.bekament.com](http://www.bekament.com)

<b>TECHNICAL DATA SHEET</b>	Issue: 1	Version: 2
<b>BK-LIV 30</b>	<b>RZ-TLP-151</b>	<b>Date: 24.12.2021.</b>

<b>Packaging, kg</b>	25
----------------------	----

## 5. OTHER CHARACTERISTICS

**Physical appearance:** Grey powder  
**pH value of the wet mass** 11-13

## 6. SURFACE PREPARATION

The surface onto which the mass is applied must be firm, clean, grease-free, with sections of low adhesion and free of dust. Before applying BK-Liv 30, it is necessary to impregnate the surface with BK-Ultra Prime substrate while in the case of application on old ceramic tiles, use BK-Bond as a base. All concrete substrates are suitable (at least 3 months old), as well as cement screed, etc.

## 7. PREPARATION AND APPLICATION

Mass is prepared by adding powder in about 19-20% of water (5 l of the water for 25 kg of powder) until complete homogenization. The mass should be left for 5 minutes, and then stirred again. The mass is applied onto the surface using a trowel or similar tools. Be especially careful around corners. After applying the mass, it is desirable to run a specialized jagged roller (comb) across the surface in order to remove any air pockets. Passability after 6 hours. It is very important to follow the recommendations related to the amount of water it takes for mixing. Greater amounts of water contribute to better spreads. This, however, also may reduce the mechanical properties of the material and cause cracks.

For larger surfaces or floors with underfloor heating, it is necessary when installing BK-Liv 30 to leave expansion joints on every 25-30m<sup>2</sup> of surface, which are filled with appropriate elastic material.

The maximum layer thickness is 30 mm and the minimum 5 mm.

## 8. CLEANING THE TOOLS

All tools must be thoroughly washed using water immediately after use. If the tools are not washed immediately after use, remove the hardened residue mechanically.

## 9. HANDLING AND STORAGE

The material must be transported in sealed bags. If the product is used in closed rooms, make sure the space is well ventilated. Protect your eyes and skin when working with the wet mass due to an alkaline reaction. Keep out of reach of children.

Store the material in dry rooms, on pallets, protected from moisture.

Shelf life: 12 months.

<b>TECHNICAL DATA SHEET</b>	Issue: 1	Version: 2
<b>BK-LIV 30</b>	<b>RZ-TLP-151</b>	<b>Date: 24.12.2021.</b>

## 10. PERSONAL PROTECTION

Respiratory tract protection: In case the process causes excessive dust, use a face mask.  
Hands and body protection: Use safety gloves. Wash hands using water each time the work is interrupted. Use long-sleeve work overalls.

Eye protection: Use safety goggles in order to protect the eyes from the dust and wet mass.

## 11. REGULATION INFORMATION

In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, grey Portland cement is a hazardous substance. The product is therefore classified a hazardous one with the following label: Hazard



Hazard

Skin irritation, Category 2: H315

Skin sensibility, category 1: H317

Heavy eye damage, Category 1: H318

Specific target organ toxicity – one-time exposure, irritation to respiratory organs, category 3: H335

### **Notifications on hazards:**

H315 Causes skin irritation.

H317 May cause skin allergic reactions.

H318 Causes serious eye damage.

H335 May cause irritation to respiratory organs.

### **Notifications on precautionary measures**

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352 IF ON SKIN: Wash with plenty of water.

P333+P313 If skin irritation or rash occurs: Seek medical advice/opinion.

P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P304+P340 IF INHALED: Take the injured person to fresh air and place in resting position which does not obstruct breathing.

P501 Dispose of contents/packaging in accordance with national regulations.

## 12. ECOTOXICOLOGICAL INFORMATION

RZ-TLP-027

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | [www.bekament.com](http://www.bekament.com)

<b>TECHNICAL DATA SHEET</b>	Issue: 1	Version: 2
<b>BK-LIV 30</b>	<b>RZ-TLP-151</b>	<b>Date: 24.12.2021.</b>

Based on experiences and information currently available, no negative health effects are known when the product is used appropriately. Prevent uncontrolled discharge into waterways because an alkaline reaction may occur.

### 13. STORAGE

In accordance with local/regional/European/national regulations.

### 14. OTHER INFORMATION

If the contractor notices an aesthetic or application deficiency while using the mass, he is obliged to cease the works and notify the manufacturer of this. The manufacturer will consider the claim in the shortest possible time frame. Complaints to the manufacturer upon using a significant portion or the entire amount of the materials are not subject to claims.

### 15. NOTE

Banja Komerc Bekament DOO performs product quality checks using its own laboratories. It also occasionally tests its products in independent certified laboratories. The Data Sheet is the product of our knowledge and previous practical experience. The purpose of the Data Sheet is to serve as a recommendation in order to achieve the best possible results. If weather and other conditions are different than those described in our instructions, our instructions need to be taken as general guidelines, without an installation warranty.

Banja Komerc Bekament DOO assumes no liability for damages resulting from the improper use or incorrect product selection, as well as for poorly executed work. It is assumed that the contractor has mastered the techniques of installing and use of various products.

Matters written herein bind us in no way.

This document replaces all previous versions. All previous versions, starting with the listed date the document was compiled, are void.

Date: 24.12.2021.

Previous version: 1.1 – 09.12.2020.

Changed chapters: 1 and 11.